

Microstructure and Mechanical Behavior of AlCoCrFeNi HEA Particles Reinforced 6063Al Alloy Matrix Composites

Shaofeng YANG^{1,2*}, Jianan WEN¹, Jiao MO¹, Hao LIU¹, Jieyu SU¹, Yuheng MI¹

¹ School of Materials Science and Engineering, Nanjing Institute of Technology, Nanjing, China, 211167

² Jiangsu Key Laboratory of Advanced Structural Materials and Application Technology, Nanjing, China, 211167

crossref <http://dx.doi.org/10.5755/j02.ms.24209>

Received 16 September 2019; accepted 31 December 2019

Lightweight composites consisting of 6063 aluminum alloy matrix reinforced with AlCoCrFeNi high-entropy alloy (HEA) particles were fabricated by the powder metallurgy through hot pressing and hot extrusion under vacuum. A detailed microstructural characterization was carried out along with the analysis of mechanical properties. The results revealed that the observed uniform distribution of HEA powders and a good bonding strength resulted in an effective strengthening and increased plastic strain of the reinforced composite. The tensile properties of composites were effectively improved by the addition of 10 and 30 vol % of reinforcing HEA particles.

Keywords: metal matrix composites, high entropy alloy, interface bonding, mechanical properties.

1. INTRODUCTION

Aluminum matrix composites (AMCs) find a wide application as promising lightweight materials [1–3]. The mechanical properties of such composites, which have a ductile metal matrix, are improved by adding reinforcing nanoparticles, such as SiC or Al₂O₃, as well as carbon nanotubes. However, the advantages of ceramics, such as high stiffness and acceptable density, are counteracted by their poor wettability/bonding with the alloy matrix, which produces a series of problems such as weak interfacial bonding strength, porosity, as well as detrimental interfacial reactions [4]. This poor interfacial bonding mechanism may deteriorate the stress resistance and mechanical properties of composites. Despite significant efforts on the improvement of interfacial bonding between the ceramics and metal matrix, no breakthrough solution to this problem has been reported yet.

Multi-principal-element alloys, also referred to as high-entropy alloys (HEAs) because of the high entropy of mixing of alloying elements, have received a considerable attention from the scientific community in the last decade [5–7]. HEAs display lucrative properties, such as excellent corrosion resistance, high hardness, superior compressive strength, excellent wear resistance, high-temperature softening resistance, etc. However, like other metallic glasses and intermetallic compounds, these brittle materials have extremely limited plasticity under stress conditions, especially HEAs with the body-centered cubic (bcc) lattice that possess higher strength and hardness. Wang et al. [8] successfully produced Al-based metal matrix composites reinforced with Mg₆₅Cu₂₀Zn₅Y₁₀ metallic glass particles that were uniformly distributed along the composite volume and exhibited a good interfacial bonding with matrix. Recent studies on HEAs have shown that the content of Al element was the key

factor for the formation of bcc solid-solution high-entropy alloy and directly influenced the alloy strength and hardness. Therefore, the brittleness of Al-containing HEA may have a good compatibility with a soft Al-based metal matrix. Given this, HEAs with bcc lattice may be good candidates for the replacement of ceramic particles as reinforcements of AMCs.

In this paper, the AlCoCrFeNi HEA particles were used as reinforcement in AMCs by Hot extrusion molding technology. The microstructure and mechanical properties were investigated by universal testing machine. A significant improvement of mechanical properties of the obtained composites was observed.

2. EXPERIMENTAL

The master alloy of the eutectic AlCoCrFeNi (elements in atomic ratios) was prepared from commercially pure elements (99.99 wt.% for Al, Co, and Ni; 99.96 wt.% for Cr and Fe). Pre-alloyed AlCrFeCoNi spherical powder with a size distribution ranging from 20 to 60 μm was provided by the vacuum induction melting and inert gas atomizer (VIGA). And 6063Al powders with 40 μm mixed with pre-alloyed AlCrFeCoNi spherical powder. The consolidation of bulk samples was prepared by a uniaxial hot pressing at 453 K with the pressure of 600 MPa, with the following hot extrusion in the argon gas environment. During the molding process, powders were heated up to 723 K at a heating rate of 30 K/min, and then a pressure of 600 MPa was applied for 10 min. And then, the samples were extruded (with the extrusion ratio of 11:1) at 723 K with a pressure of 600 MPa.

The microstructural characterization of the crystal structure was carried out by a scanning electron microscopy (SEM, FEI Quanta 200, EDS, IE350MT) and Bruker D8 ADVANCE X-ray diffractometer (XRD) with a Cu K-α radiation target. Tensile tests were conducted using an Instron 5500 testing system. The Vickers hardness measurements were carried out on the consolidated sample


*Corresponding author. Tel.: +86-25-86118274; fax: +86-25-86118271.
E-mail address: yangshf@njit.edu.cn (S.F. Yang)

with the load of 300 gf with the dwell time 10s using a Digital MicroHardness Tester HVS-1000.


3. RESULTS AND DISCUSSION

3.1. XRD and microstructure analysis

The SEM morphologies of the pre-alloyed AlCrFeCoNi spherical powders are shown in Fig. 1 a. It can be obviously seen that there are uniform spherical powders, which can improve the fluidity of powder in the printing process, and the surface of the particle is obviously equiaxial crystals after solidification (as shown in inset). The XRD pattern of the AlCrFeCoNi HEA is shown in Fig. 1 b.



a



b

Fig. 1. a – SEM morphologies of AlCrFeCoNi HEA powders; b – XRD patterns of the AlCrFeCoNi HEA

It can be seen from the figure that the printed alloy is composed of simple BCC solid solution which similar to the Fe–Cr solid solution (PDF#34-0396). It is indicated that no complex multiphase forms in the alloys. The XRD pattern of the composite reinforced with 30 vol.% of HEA is shown in Fig.2. The pattern displays peaks corresponding to Al lattice.

Several physical parameters have been proposed to predict structural stability and phase formation in HEAs. Zhang et al [9] suggested a criterion for achieving solid-solution phases in HEAs using three parameters, ΔS_{mix} (entropy of mixing) ΔH_{mix} (enthalpy of mixing) and δ (atomic radius difference), as expressed below:

$$\delta = \sqrt{\sum_{i=1}^n c_i (1 - r_i / \bar{r})^2}, \quad (1)$$

where c_i is the atomic percentage of the i^{th} component; $\bar{r} = \sum_{i=1}^n c_i r_i$ is the average atomic radius; r_i is the atomic radius of the i^{th} component.




Fig. 2. XRD patterns of hot pressed Al-based composites with 30 vol.% HEA particles

The thermodynamic parameter (Ω) is defined as:

$$\Omega = \frac{T_M \Delta S_{mix}}{|\Delta H_{mix}|}, \quad (2)$$

where, $T_m = \sum_{i=1}^n c_i (T_m)_i$, $(T_m)_i$ is the melting point of the i^{th} component.

The mixing enthalpy (ΔH_{mix}) can be represented by:

$$\Delta H_{mix} = \sum_{i=1, i \neq j}^n \Omega_{ij} c_i c_j, \quad (3)$$

where $\Omega_{ij} (= 4\Delta H_{ij}^{mix})$ is the regular solution interaction parameter between the i^{th} and j^{th} elements; c_i and c_j are the atomic percentages of the i^{th} and j^{th} component. It is to be noted that ΔH_{mix}^{ij} is the enthalpy of mixing, obtaining on the basis of Miedema macroscopic model for binary liquid alloys; and mixing entropy (ΔS_{mix}) can be represented by:

$$\Delta S_{mix} = -R = \sum_{i=1}^n c_i \ln c_i, \quad (4)$$

where c_i is the mole percent of component, $\sum_{i=1}^n c_i = 1$; R is the gas constant ($= 8.314 \text{ J}^{-1} \text{ K mol}^{-1}$).

The parameters, ΔS_{mix} , ΔH_{mix} , δ for the AlCrFeCoNi HEA are $13.09 \text{ J} \cdot \text{mol}^{-1} \text{ K}^{-1}$, $-12.78 \text{ KJmol}^{-1}$, 5.28 , respectively. The presence of the BCC phase implies that the mechanical alloying AlCrFeCoNi powder results in a more stable phase than FCC phase or intermetallic compounds in virtue of high mixing entropy.

Fig. 3 shows the SEM and TEM micrographs of the consolidated composites with 30 vol.% HEA. As shown in Fig. 3 a, it can be clearly seen that HEA particles are uniformly distributed on the underground of the Al alloy matrix. The Fig. 3 b presents the interface between the HEA particle and the Al metal matrix. A clean and dissolving diffusion surface between the HEA particles and the matrix phases could be observed and the obtained

composite materials have high density with few pores are visible. Especially at the interface, the Al matrix is tightly bound to the HEA reinforcement, and micro-reactions occur between the two phases, forming a lamellar layer of intermetallic compounds, suggesting that the AlCrFeCoNi HEA has good affinity with the matrix. Fig. 3 c shows the interface at a higher magnification. It can be found a diffusion reaction layer of 1–4 nm between matrix aluminum and high entropy alloy. It is well known that in solid phase sintering, the solid solubility between aluminum and transition group metal elements is very low, while the diffusion reaction between aluminum and iron and other elements requires a large solid solubility. The reaction layer in Fig. 3 c between aluminum alloy and high entropy alloy can be attributed to the following factors: the high entropy alloy solid solution state and the larger lattice distortion in high entropy alloys.




Fig. 3. Micrographs for the hot-pressed composites with 30 vol.% of HEA reinforcement: a–SEM micrographs; b–the interface between the HEA particle and the Al metal matrix; c–the interface at a higher magnification

Appropriate interfacial reactions are beneficial to transfer loads and improve mechanical properties of composites [8].

3.2. Mechanical properties

Fig. 4 depicts the stress-strain curve of tensile specimen constructed under tensile loading to the hot-pressed 6063 Al alloy and composite materials with 10 and 30 vol.% of HEA particles. The tensile samples are shown in the insert to Fig. 4 a. The hot-pressed 6063 Al alloy has excellent tensile mechanical properties, namely, yield strength of 155 ± 10 MPa, ultimate tensile strength of 190 ± 10 MPa, and plastic strain of 14.2 ± 0.5 %, which are higher than those of 6063 T5 alloy (145 MPa, 185 MPa, and 12 %, respectively). In contrast to cast samples from 6063Al alloys, the ones produced from hot-pressed and hot-extruded powders have smaller crystalline grains and enhanced texture, which ensure improved mechanical properties of the metal matrix and make it lucrative for the AMC formation.




Fig. 4. a–stress-strain curves for 6063 Al; b–for the AMCs with 10; c–30 vol.% of AlCrFeCoNi HEA particles

The mechanical properties of hot-pressed 6063 Al alloy are significantly improved by the FeNiCoCrCuAl_{2.8} HEA particles: the yield strength and ultimate tensile strength are increased from 155 ± 10 and 190 ± 10 MPa pure 6063 Al alloy, respectively, to 185 ± 10 and 245 ± 10 MPa to 10 vol.% HEA aluminum matrix composites. The samples with 10 vol.% of HEA also obtains a considerable strain rate (11.2 ± 0.5 %) before failure. With an increase in the volume fraction of HEA powders to 30 vol.%, the yield strength and ultimate tensile strength further rose to 350 ± 10 and 475 ± 10 MPa, respectively. Quite unexpectedly, the plastic strain of AMC with 30 vol.% HEA is increased to 16.1 ± 0.5 %. Reinforcing particles with high hardness greatly increased the yield strength of the AMC matrix. Besides the qualitative changes in the morphology, the quantitative estimation of the yield strength of AMCs reinforced with uniformly distributed hard particles can be provided as follows [10]:

$$\sigma_{COH} = M\varepsilon^{3/2}G\left(\frac{rf}{b}\right)^{1/2}, \quad (5)$$

where M is a constant ranging from 2.6 to 3.7; ε denotes the mismatch strain at the coherent interface; G is the matrix shear modulus; r is the particle radius; f is the volume fraction of particles; b is the modulus of Burgers vector of the matrix dislocation. The hardness and yield strength improvement accompanied by an increase in the volume fraction of AlCrFeCoNi HEA particles is shown in Table 1. As seen in Table 1, the yield strength values of AMCs calculated via Eq. 5 are in excellent accordance with the experimental results.

Table 1. Yield strength and hardness tabulation of 6063 Al alloys and their composites

	Hardness, HV	Yield strength, MPa	Estimated by Eq. 1, MPa
6063 alloys	48.68	155	
AlCrFeCoNi HEA	655	254 (compression)	
10 vol.% HEA of AMCs	116.45	245	234
30 vol.% HEA of AMCs	129.90	475	458

Fig. 5 shows the corresponding fracture morphologies of the 6063Al alloy and AMCs. The tensile strain rate of the notched specimen was relatively low, the 6063Al alloy specimen fracture originated in the specimen center. The dominating macro- and microfracture mode was ductile: a pronounced necking as observed at the macrolevel, as well as multiple equiaxed dimples and a few tear ridges near the specimen edges at the microlevel, as shown in Fig. 5 a and b. The respective fractographic features of the AMC samples with different volume fraction of HEA particles are depicted in Fig. 5 c to f. In contrast to the fracture morphology of 6063 aluminum alloy, dimples in the composite correspond to peel-off sites of the reinforcing phase, tear ridges are observed at the reinforcing phase edges, and the fracture zone of the aluminum alloy matrix between the reinforcing phases contains equiaxed dimples. As compared to Fig. 5 d and f, the positions of

AlCrFeCoNi HEA particles are shallower, and the interface between the particles and the matrix is less pronounced. Moreover, the fracture morphology of the aluminum alloy matrix is characterized by uniformly distributed tiny dimples. An increase in the HEA volume fraction from 10 to 30 vol.% resulted in the growth of the yield strength and strain by 93.9 and 43.8 %, respectively. This improvement can be attributed not only to good wettability and, hence, a strong interfacial bonding strength, but also to the uniform HEA distribution in the matrix.




Fig. 5. Fracture images of the samples: a, b – 6063 Al; c, d – 10 vol.% HEA; e, f – 30 vol.% HEA

4. CONCLUSIONS

6063Al composites reinforced with different volume fractions of AlCrFeCoNi particles were prepared by hot extrusion. The high-entropy alloy (HEA) systems are mainly composed of bcc solid solution. The HEA-reinforced composites have good bonding with the matrix. The excellent mechanical properties of the high-entropy alloy composites are attributed to good wettability and, hence, strong interfacial bonding achieved between the matrix and HEA particle interface. The tested samples from composites with 30 vol.% HEA exhibited excellent mechanical properties, namely the yield strength of 350 ± 10 MPa, ultimate tensile strength of 475 ± 10 MPa, and plastic strain of 16.1 ± 0.5 %. Thus, as compared with the matrix, the hardness and yield strength of the composites under study were significantly improved, with a notable increase of plasticity.

Acknowledgments

This study was supported by National Natural Science Foundation of China [51671104], the Fourteenth batch of

six Top Talent projects of Jiangsu Province [XCL-032], Challenge Cup cultivation Project for College students' Innovation Project in Nanjing Institute of Engineering [TP20180003].

REFERENCES

1. **Shojaei, K., Sajadifar, S.V., Yapici, G.G.** On the Mechanical Behavior of Cold Deformed Aluminum 7075 Alloy at Elevated Temperatures *Materials Science & Engineering A* 670 2016: pp. 81–89. <https://doi.org/10.1016/j.msea.2016.05.113>
2. **Otto, F., Dlouhý, A., Somsen, C., Bei, H., Eggeler, G., George, E.P.** The Influences of Temperature and Microstructure on the Tensile Properties of a CoCrFeMnNi High Entropy Alloy *Acta Materialia* 61 2013: pp. 5743–5755. <http://dx.doi.org/10.1016/j.actamat.2013.06.018>.
3. **Wang, Z., Scudino, S., Prashanth, K.G., Eckert, J.** Corrosion Properties of High-strength Nanocrystalline Al₈₄Ni₇Gd₆Co₃ Alloy Produced by Hot Pressing of Metallic Glass *Journal of Alloys and Compounds* 707 2017: pp. 63–67. <http://dx.doi.org/10.1016/j.jallcom.2016.11.21>
4. **Fa, Q.C., Li, B.S., Zhang, Y.** The Microstructure and Properties of (FeCrNi)Al_xCu_y High-Entropy Alloys and Their TiC-reinforced Composites *Materials Science & Engineering A* 598 2014: pp. 244–250. <http://dx.doi.org/10.1016/j.msea.2014.01.044>
5. **Zhang, Y., Zuo, T.T., Tang, Z., Gao, M.C., Dahmen, A., Liaw, P.K., Lu, Z.P.** Microstructures and Properties of High-entropy Alloys *Progress in Materials Science* 61 2014: pp. 1–93. <http://dx.doi.org/10.1016/j.pmatsci.2013.10.001>
6. **Fu, Z.Q., Chen, W.P., Wen, H.M., Zhang, D.L., Chen, Z., Zheng, B.L., Zhou, Y.Z., Lavernia, E.J.** Microstructure and Strengthening Mechanisms in an FCC Structured Single-phase Nanocrystalline Co₂₅Ni₂₅Fe₂₅Al_{7.5}Cu_{17.5} High Entropy Alloy *Acta Materialia* 107 2016: pp. 59–71. <http://dx.doi.org/10.1016/j.actamat.2016.01.050>
7. **Ogura, M., Fukushima, T., Zeller, R., Dederichs, P.H.** Structure of the High-entropy Alloy Al_xCrFeCoNi: Fcc Versus Bcc *Journal of Alloys and Compounds* 715 2017: pp. 454–459. <http://dx.doi.org/10.1016/j.jallcom.2017.04.318>
8. **Wang, Z., Tan, J., Sun, B.A.** Fabrication and Mechanical Properties of Al-Based Metal Matrix Composites Reinforced with Mg₆₅Cu₂₀Zn₅Y₁₀ Metallic Glass Particles *Materials Science & Engineering A* 600 2014: pp. 53–58. <http://dx.doi.org/10.1016/j.msea.2014.02.003>
9. **Okamoto, N.L., Fujimoto, S., Kambara, Y., Kawamura, M., Chen, Z.M.T., Matsunoshita, H., Tanaka, K., Inui, H., George, P.** Size Effect, Critical Resolved Shear Stress, Stacking Fault Energy, And Solid Solution Strengthening in the CrMnFeCoNi High-entropy Alloy *Scientific Reports* 6 2016: pp. 35863. <http://dx.doi.org/10.1038/srep35863>.
10. **Wang, Z., Georgarakis, K., Nakayama, K.S.** Microstructure and Mechanical Behavior of Metallic Glass Fiberreinforced Al Alloy Matrix Composites *Scientific Reports* 2016: pp. 1–11. <http://dx.doi.org/10.1038/srep24384>



© Yang et al. 2021 Open Access This article is distributed under the terms of the Creative Commons Attribution 4.0 International License (<http://creativecommons.org/licenses/by/4.0/>), which permits unrestricted use, distribution, and reproduction in any medium, provided you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made.